Europäisches Patentamt

European Patent Office

Office européen des brevets



(11) EP 1 227 137 A1

(12)

### **EUROPEAN PATENT APPLICATION**

(43) Date of publication: 31.07.2002 Bulletin 2002/31

(51) Int Cl.7: C09D 11/02

(21) Application number: 02000173.1

(22) Date of filing: 09.01.2002

AL LT LV MK RO SI

(84) Designated Contracting States:

AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU

MC NL PT SE TR

Designated Extension States:

(30) Priority: 26.01.2001 JP 2001018705

(71) Applicant: RISO KAGAKU CORPORATION
Tokyo (JP)

(72) Inventors:

 Ogawa, Hiroyuki, Riso Kagaku Corp., R&D Center
 Inashiki-gun, Ibaraki-ken (JP)

 Takayama, Hideaki, Riso Kagaku Corp., R&D Center

Inashiki-gun, Ibaraki-ken (JP)

(74) Representative: HOFFMANN - EITLE Patent- und Rechtsanwälte Arabellastrasse 4 81925 München (DE)

### (54) Emulsion ink for stencil printing and its use

(57) An emulsion ink for stencil printing comprises 20 to 50 wt.% of an oil phase and 50 to 80 wt.% of a water phase, and contains at least one kind of a vegetable oil with an iodine number ranging from 110 to 150 in the oil phase at least in an amount indicated by the following formula in wt.%, and an antioxidant in an amount ranging from 1 to 10 wt.% based on the content of the vegetable oil:

Minimum amount of vegetable oil in wt.% = amount of water in ink in wt.% x (100/iodine number) x 0.09.

The ink causes no clogging or offset when a printer is not in operation and the ink is left in a printing drum of the printer for a long period of time.

Disclosed is also a printed matter printed by the emulsion ink of the present invention.

Vegoil not esterified

EP 1 227 137 /

### Description

20

30

#### BACKGROUND OF THE INVENTION

#### 1. Field of the Invention

[0001] The present invention relates to an emulsion ink for use in stencil printing, particularly to an emulsion ink containing a vegetable oil, and to a printed matter printed by the emulsion ink for stencil printing.

### 2. Description of the Related Art

[0002] In the stencil printing method, a stencil master is prepared by perforating a stencil sheet in accordance with a desired image, and ink is passed through a perforated portion of the stencil sheet, thereby printing on an image-receiving medium such as paper. Stencil printing is utilized for a variety of purposes because of its ease of handling and convenience.

[0003] As the ink for stencil printing, a water-in-oil (W/O) type emulsion ink is mainly used. A high-boiling point solvent such as a nondrying oil or a nonvolatile mineral oil is used for the emulsion ink for its oil phase, thus preventing so-called clogging in which the ink dries and solidifies on a printing drum of a printer and at the perforated portion of a stencil sheet, which hinders the ink from passing through the stencil sheet, when the printer is not in operation for a long period of time. On the other hand, when the ink is left in a printing drum of a printer for a long period of time, water content in the ink evaporates since the ratio of a water phase as an inner phase of the emulsion is relatively high. The ratio between an oil phase and the water phase becomes unbalanced, and ink viscosity decreases. As a result, an excessive amount of ink is transferred to printing paper when printing is restarted. Accordingly, problems occur such as increased image density and an offset phenomenon (unintentional transfer of an inked impression from printed surface of one printing paper to the reverse side of another printing paper by contact).

[0004] In order to solve these problems, Japanese Patent No. 2096338 proposes the use of a solvent having a boiling point of 180 to 270°C. Additionally, Japanese Unexamined Patent Application Publication No. 5-125320 proposes the use of a solvent that consists of 10 to 30 wt.% of a volatile solvent with an initial boiling point of 150 to 210°C and 70 to 90 wt.% of a nonvolatile solvent. These proposals are intended to prevent changes in the ratio between a water phase and an oil phase of an emulsion ink and to prevent a decrease in ink viscosity by adding each specified amount of each solvent having the specified range of boiling point or initial boiling point, so as to allow a small amount of the solvent as an oil component to evaporate, along with evaporation of the water content in the ink.

[0005] However, even when no problems would occur in the above ink after standing not in operation at an ordinary temperature (23°C) for one week or one month, clogging may occur due to the evaporation of a solvent when the environmental temperature rises. Also the evaporation of the solvent may damage health of printing operators and ink manufacturers.

[0006] On the other hand, ink using a vegetable oil has recently attracted attention as an environment-consciously developed printing ink. For instance, Japanese Unexamined Patent Application Publication No. 10-245516 proposes a water-in-oil type emulsion ink for stencil printing using a vegetable oil which has an iodine number of 100 or less and a congeal point (freezing point) of 0°C or below. This ink uses a nondrying oil with an iodine number of 100 or less in order to prevent the ink from solidifying. However, when the ink is left for a long period of time, water content in the ink may evaporate and the viscosity of the ink may decrease, thereby causing excess transfer of ink and offset.

### SUMMARY OF THE INVENTION

[0007] It is therefore an object of the present invention to provide an emulsion in which causes neither clogging nor offset after a long nonuse period of time, has shelf stability and is harmless to environment and ink handlers. Here, "a long nonuse period of time" refers to the condition under which a printer is not in operation and ink is allowed to stand in a printing drum of the printer for a long period of time. Another object of the present invention is to provide a printed matter having a desirable printing image and no offset after a long nonuse period of time.

[0008] The present inventors focused on the oxidation phenomenon of a vegetable oil and its iodine number as an index for the unsaturation degree of the vegetable oil. They found that an emulsion ink for stencil printing, which causes neither clogging nor offset after a long nonuse period of time and has shelf stability, can be provided by mixing a vegetable oil with an iodine number ranging from 110 to 150 in a specific amount or more relative to the water amount in the ink, and furthermore, by mixing an antioxidant in a specified range based on the amount of the vegetable oil mixed.

[0009] Specifically, awater in the ink of the present invention in the ink of the invention in the ink of the

and an antioxidant in a range of 1 to 10 wt.% based on the content of the vegetable oil:

Minimum amount of vegetable oil in wt.% = amount of

water in ink in wt.%  $\times$  (100/iodine number)  $\times$  0.09

(1)

[0010] According to the present invention, a change in ink viscosity due to water evaporation can be prevented by controlling an increase in viscosity due to the oxidation of the vegetable oil in the ink, providing an emulsion ink for stencil printing which causes no clogging or offset after a long nonuse period of time and which has shelf stability. Furthermore, the use of a vegetable oil enables one to provide an ecologically superior ink that is designed for reducing environmental damage and improving safety of printing operators and ink manufacturers.

[0011] In another aspect, the present invention provides a printed matter printed by the emulsion ink mentioned above. By utilizing the emulsion ink of the present invention, a printed matter having a desirable printing image and no offset can be produced after a long nonuse period of time.

#### DESCRIPTION OF THE PREFERRED EMBODIMENTS

5

10

20

45

50

[0012] Awatersinsolitypetermulsioniints for use in stencil printing (mentioned as "ink" hereinafter) relating to the present invention includes 2016 150 Wit Antionian to liphase rand 80 to 50 Wit Antionian to 150 at least in the minimum amount specified by the above formula (1) relative to the water content in the ink. The semidrying or drying vegetable oil contained is oxidized after a long nonuse period of time, thereby increasing ink viscosity. Accordingly, a decrease in ink viscosity due to water evaporation from the ink can be controlled, and excess ink transfer and offset (and deterioration of such offset) after a long nonuse period of time can be prevented. Furthermore, since the ink contains the antioxidant in the specified amount based on the amount of the vegetable oil, drying solidification due to excess oxidation of the vegetable oil can also be prevented. As a result, the emulsion ink is free of clogging after a long nonuse period of time and its shelf stability is maintained.

[0013] Here, the regetable contained in any phase, whereas the antioxidant may be contained in any phase, such as an oil phase, a water phase, and oil and water phases. The phase in which the antioxidant is contained can be properly selected based on the kind of antioxidant and the solubility thereof in a water phase or an oil phase.

[0014] The <u>wegetable followith</u> an iodine number ranging from 110 to 150 is a semidrying oil or a drying oil. Examples thereof include <u>soybean oil compoil sunflower follower oil safflower oil safflower oil graperseed oil sesame foil and the Ilike. Each of these vegetable oils be used singly or in combination with one or more kinds thereof.</u>

[0015] When the iodine number of the vegetable oil is 110 or above, an appropriate increase in ink viscosity due to the oxidation of the vegetable oil can be obtained. This increase can control and compensate a decrease in ink viscosity due to water evaporation after a long nonuse period of time. As a result, at the starting of printing (the rising time) after a nonuse period, excess ink transfer can be prevented. Further, when the iodine number is 150 or less, clogging due to a sharp increase in the viscosity and drying solidification of the vegetable oil can be prevented even after a long nonuse period of time. A vegetable oil having an iodine number of more than 150 has high polarity, so that the solubility balance of an oil phase tends to be destroyed and the shelf stability of the emulsion ink may deteriorate.

[0016] The vegetable oil is contained at least in an amount expressed by the following Formula (1) relative to an amount of water in ink in wt.%:

Minimum amount of vegetable oil in wt.% = amount of

water in ink in wt.%  $\times$  (100/iodine number)  $\times$  0.09 (1)

[0017] Since the iodine number indicates an unsaturation degree (double bond content) in 100 g of fatty acid, the present inventors considered the amount of vegetable oil  $\times$  (iodine number/100) as an index for an increase in the viscosity of the vegetable oil. The inventors presented a new view that a decrease in the ink viscosity due to water evaporation can be effectively prevented when the index is at a certain rate or above relative to the amount of water, and experimentally found a coefficient of 0.09. Finally, Formula (1) mentioned above was derived therefrom. When the coefficient is less than 0.09, the effects of the present invention cannot fully be obtained. When the amount of a vegetable oil is that specified by the above Formula (1) or more, a decrease in the ink viscosity after a long nonuse period of time can effectively be avoided, preventing excess ink transfer and offset. The maximum content of the vegetable oil is controlled so that an oil phase ratio is adjusted to 20 to 50 wt.% in the ink. Since the antioxidant is mixed in an

amount ranging from 1 to 10 wt.% based on the amount of the vegetable oil mixed in an amount of the above Formula (1) or more, an increase in the viscosity of the vegetable oil can be controlled, if necessary, by adjusting the amount of the antioxidant depending on the amount of the vegetable oil and the iodine number thereof. It is preferable that the content of the vegetable oil is 20 wt.% or less, or more preferably, 15 wt.% or less based on the total weight of ink in order to secure the stability of the emulsion.

[0018] An adequate known antioxidant such as dibutylhydroxytoluene, propyl gallate, octyl gallate, tocopherol and butylhydroxyanisole is employable as the antioxidant. Each of them can be used singly or in combination thereof. Moreover, a water-soluble antioxidant such as sodium erythorbate and sodium ascorbate may be added to a water phase of the ink.

[0019] The antioxidant is added in a range of 1 to 10 wt.% based on the content of the vegetable oil. When the content is 1 wt.% or more, the drying solidification of the vegetable oil after a long nonuse period of time can be avoided, thereby preventing clogging. On the other hand, when the content exceeds 10 wt.%, the oxidation of the vegetable oil after a long nonuse period of time may be inhibited excessively and a sufficient increase in ink viscosity for inhibiting a decrease in ink viscosity may not be obtained, and besides, the stability of emulsion may be damaged.

[0020] In addition to the above-noted vegetable oil and antioxidant (in the case of mixing to an oil phase), other components such as an oil component other than the vegetable oil mentioned above, a surfactant, a coloring agent, an extender pigment, etc. can be mixed in an oil phase. Furthermore, it is preferable that a resin is contained. The coloring agent may be contained in a water phase or both water and oil phases.

[0021] The oil component, other than the vegetable oil with an iodine number ranging from 110 to 150, can be, for example, a nondrying oil such as castor oil, tsubaki oil, olive oil, coconut oil and palm oil; a mineral oil such as liquid paraffin, spindle oil, gas oil, kerosene, machine oil, lubricating oil and synthetic fluid; and a petroleum-based solvent such as olefinic hydrocarbon and aromatic hydrocarbon. Each of the oil components can be used singly or in combination thereof. The oil component is contained in such an amount that the whole amount of an oil phase containing a vegetable oil with an iodine number ranging from 110 to 150 and other additives as required is adjusted to 20 to 50 wt.%.

[0022] Examples of the surfactant include anionic surfactants such as a metallic soap, a sulfate ester salt of higher alcohol, and a sulfate ester salt of polyoxyethylene adduct; cationic surfactants such as primary, secondary and tertiary amine salts, and a quaternary ammonium salt; ether type nonionic surfactants such as a polyoxyethylene ether of higher alcohol, an alkylphenol polyoxyethylene ether, and polyoxyethylene ether of polyoxypropylene; ester type nonionic surfactants consisting of polyhydric alcohols and fatty acids, such as a sorbitan fatty acid ester and a polyglycerol fatty acid ester; ether ester type nonionic surfactants such as a polyoxyethylene ether of fatty acid, a polyoxyethylene ether of polyglycerol fatty acid ester, and polyoxyethylene ether of castor oil; and nitrogen-containing type nonionic surfactants such as an alkylolamide of fatty acid. Each of the surfactants can be used singly or in combination with one or more kinds thereof. The amount thereof can be properly determined based on the molar concentration of each surfactant, the area of an interface of a water phase and an oil phase, and partially the area of an interface of an oil phase and a solid such as a pigment. Generally, the amount is preferably about 0.1 to 10 wt.%, and more preferably, about 1 to 5 wt.% based on the total weight of the ink.

[0023] Examples of the coloring agent include organic pigments such as an insoluble azo pigment, a soluble azo pigment, phthalocyanine blue, dye lake, isoindolinone, quinacridone, dioxazine violet, perinone, and perylene; inorganic pigments such as carbon black and titanium dioxide; azo-based, anthraquinone-based or azine-based oil-soluble dyes; water-soluble dyes, and disperse dyes. Each of the coloring agents can be used singly or in combination with one or more kinds thereof so as to achieve the required hue, and may be a mixture of pigment and dye. Although the amount thereof can appropriately be set, it is in general preferably 20 wt.% or less, and more preferably, 3 to 10 wt.% based on the total weight of the ink.

[0024] Examples of the resin include phenol resins, maleic acid resins, petroleum resins, rubber resins, alkyd resins, and rosin-modified resins. Each of them can be used singly or in combination with one or more kinds thereof. The resin can add viscosity to the ink and improve the stability of the emulsion. Moreover, when an oil phase contains a pigment or extender pigment, their dispersibility in the ink and their fixing property to the printing paper can be improved.

[0025] In addition to the above, a known pigment dispersant can be added to the oil phase of the ink as long as the preparation and stability of the emulsion are not disturbed. A compound containing a wax or the like as a main component may also be added as an auxiliary agent to adjust the fluidity.

[0026] Next, a water phase of the ink can contain a known component such as a oil-in-water (O/W) type resin emulsion, a water soluble resin, a wetting agent, an electrolyte, an antioxidant, a pH adjustor, an antifreezing agent, etc.

[0027] Examples of the oil-in-water type resin emulsion include polyvinyl acetate, ethylene-vinyl acetate copolymer, vinyl acetate-acrylic ester copolymer, polymethacrylic ester, polystyrene, styrene-acrylate ester copolymer, styrenebutadiene copolymer, vinylidene chloride-acrylate ester copolymer, vinyl chloride, vinyl chloride-vinyl acetate copolymer, and urethane. Each of the resins can be used singly or in combination with one or more kinds thereof.

[0028] Examples of the water soluble resin include polyvinyl alcohol, methyl cellulose, carboxymethyl cellulose, hydroxyethyl cellulose, polyvinyl pyrrolidone, polyethylenepolyvinyl alcohol copolymer, polyethylene oxide, polyvinyl

ether, polyacrylamide, gum arabic, starch, and water soluble urethane. Each of the resins can be used singly or in combination with one or more kinds thereof.

[0029] The total mixing amount of the oil-in-water type resin emulsion and/or water soluble resin is, in terms of solid content, preferably 20 wt.% or less, and more preferably, 10 wt.% or less based on the total weight of the ink in order to ensure the ink permeability. Such resin component can improve the wettability and dispersibility of the pigment and extender pigment, and their fixing property to the printing paper.

[0030] Examples of the wetting agent include polyhydric alcohols such as ethylene glycol, sorbitol and glycerol, and polyethylene glycol.

[0031] Examples of the electrolyte include sodium sulfate, magnesium sulfate, potassium hydrogenphosphate, sodium citrate, potassium tartrate, and sodium borate.

[0032] Examples of the antifreezing agent (a vaporization-suppressive component) include polyhydric alcohols such as ethylene glycol and propylene glycol, and alkyl ethers of polyhydric alcohols such as ethylene glycol monoethyl ether. [0033] The oil phase and the water phase each including the above-noted components are mixed with the respective ratios of (20 to 50 wt.% of the oil phase) to (80 to 50 wt.% of the water phase). Both phases are mixed and emulsified to make the ink. It is preferable that the water phase and the oil phase are separately prepared, then the water phase liquid is added to the oil phase liquid and emulsified. A known emulsifier such as a dispersion mixer, a homo mixer and a high pressure homogenizer can be used for the ink manufacture.

[0034] A printed matter relating to the present invention is printed using the ink of the present invention mentioned above.

[0035] As an image-receiving medium (a substrate to be printed) of the printed matter, for example, any printing paper can be used with no special limitation. The stencil printing using the ink of the present invention can be carried out by using a known stencil printer. The design and operating conditions of the printer are not particularly limited.

[0036] The present invention will be explained below in further detail by referring to the embodiments. In the following description, "parts" indicate "weight parts".

1. Preparation of ink

25

45

55

### Examples 1 to 7, Comparative Examples 1 to 6

[0037] Each example and comparative example of ink was prepared in the following order by using the components shown in Table 1 and Table 2. First, carbon black (MA100 manufactured by Mitsubishi Chemical Corp.) and alkyd resin (ARAKYD No. 4 manufactured by Arakawa Chemical Industries, Ltd.) were dispersed using a three-roll mill, to prepare a pigment dispersion. Subsequently, a vegetable oil, a spindle oil (white spindle oil manufactured by Nippon Mitsubishi Oil Corp.), a solvent (AF6 manufactured by Nippon Mitsubishi Oil Corp., boiling point: 301 to 321°C), dibutylhydroxy-toluene and sorbitan sesquioleate were added to the dispersion as the remaining oil phase components and mixed, thus obtaining an oil phase. Meanwhile, ethylene glycol and magnesium sulfate were added to ion exchange water and mixed, thus obtaining a water phase. The water phase was gradually added to the oil phase and emulsified, thus obtaining a water-in-oil type emulsion ink for stencil printing.

Evaluation of the ink and printed matter

[0038] Using each obtained emulsion ink, a stencil printer (RISOGRAPH FR275 (trademark) manufactured by Riso Kagaku Corp.) and a printing paper (wood free paper; RISO-YOSHI, Usukuchi) manufactured by Riso Kagaku Corp., clogging property, offset property and high temperature storage stability of the ink after standing were evaluated as follows.

### A. Clogging

[0039] Printing was conducted after allowing the ink to stand in a printing drum of the printer for one month under ordinary temperature (23°C, 50% RH) or under high temperature (40°C). The evaluation was done according the following criteria:

- G: Desirable printing images were obtained during printing up to 50 sheets.
- M: Desirable printing images were obtained during printing between 50 and 100 sheets.
- NG: Clogging occurred and desirable printing images were not obtained even after printing over 100 sheets.

## B. Offset

10

15

25

30

35

40

45

50

[0040] Printing was conducted after allowing the ink to stand in a printing drum of the printer for one month under ordinary temperature (23°C, 50% RH). Rear surfaces of the first to the twentieth printed matter were visually observed. The evaluation was done according the following criteria:

- G: There was no offset.
- M: There was slight offset.
- NG: There was clear offset.
- C. High temperature storage stability

[0041] The ink was allowed to stand in a sealed system at 70°C for one week or for one month, and the state of the ink was visually observed. The evaluation was done according the following criteria:

- G: The emulsion had not disintegrated.
- M: There was slight oil floating (oil bleeding).
- NG: The emulsion had disintegrated.
- 20 [0042] The results are shown in Table 1 and Table 2.

6

Table 1

	10010 1								
	Composition/weight parts		Examples						
5		phase	1	2	3		5	6	7
		Carbon black	5.0	5.0	5.0	5.0	5.0	5.0	5.0
	Coloring agent	Caroon olack	3.0	3.0	3.0	3.0	3.0	3.0	3.0
	Resin	Alkyd resin	6.0	6.0	6.0	6.0	6.0	6.0	6.0
	Oil	Spindle oil	6.0	6.0	15.0	5.0	7.0	9.0	6.0
10	component	Solvent (AF6)	6.9	6.9	12.1	6.9	7.9	7.0	5.0
10	Vegetable	Rapeseed oil	6.0	0.5	0	0.5	0	0	0
	oil	(IN = 113)	1		j	}		•	•
		Soybean oil (IN = 130)	0	6.0	4.0	0	4.0	15.0	20.0
15		Safflower oil (IN = 145)	0	0	0	6.0	0	0	0
	Surfactant	Sorbitan sesquioleate	4.0	4.0	4.0	4.0	4.0	4.0	4.0
	Antioxidant	Dibutylhydroxy toluene	0.1	0.1	0.1	0.1	0.1	0.2	0.2
20	Water	r phase	L						
20	Water	Ion exchange Water	55.0	55.0	45.0	55.0	55.0	45.0	45.0
	Electrolyte	Magnesium sulfate	3		1.0	0.8	0.8		
	Antifreezing	Ethylene	10.0	10.0	8.0	10.0	10.0	8.0	8.0
25	agent	glycol							
	Total		100.0	100.0	100.0	100.0	100.0	100.0	100.0
	MA of vegetable oil RA of antioxidant		0.06	3.81	3.12 0.04	0.06	0.04	3.12 0.15	3.12 0.20
	KA OF antioxic	- 0.6	- 0.6	- 0.4	- 0.6	~ 0.4	- 1.5	~ 2.0	
	23		G G	G G	G G	G G	G G	G	G G
30	Clogging (23°C, 1 month)		G	G	G	G	G	G	G
•	Clogging (40°C, 1 month)					G			
	Offset (23°C, 1 month)		G	G	G		G	G	G
	High temperature storage			G	G	G	G	G	G
	stability (70°C, 1 week)								
0.5	High temperatu	-	G	G	G	G	G	G	м
35	stability (70°	C, I month)		L		لـــــــــــــــــــــــــــــــــــــ	L	لحسما	

IN: iodine number

MA of vegetable oil: Minimum amount of vegetable oil calculated from Formula (1)

RA of antioxidant: Required amount of antioxidant based on amount of vegetable oil

50

40

45

55

Table 2

Composition/w	eight parts	Ţ <u></u>	Compa	rative	Example	S	
	• •	1	2	3	4	5	6
Oil p	hase						
Coloring agent	Carbon black	5.0	5.0	5.0	5.0	5.0	5.0
Resin	Alkyd resin	6.0	6.0	6.0	6.0	6.0	6.0
Oil component	Spindle oil	10.0	1.0	6.0	6.0	7.0	5.0
	Solvent	5.95	1.7	6.99	6.0	7.8	5.9
<u> </u>	(AF6)			-	6.0	0	0
Vegetable   oil	Soybean oil (IN = 130)	3.0	4.0	6.0	6.0	"	"
	Linseed oil (IN = 170)	0	0	0	0	4.0	0
	Castor oil (IN = 86)	0	0	0	0	0	8.0
Surfactant	Sorbitan sesquioleate	4.0	4.0	4.0	4.0	4.0	4.0
Antioxidant	Dibutylhydro xytoluene	0.05	0.1	0.01	1.0	0.2	0.1
Water	phase						
Water	Ion exchange	55.0	65.0	55.0	55.0	55.0	55.0
Electrolyte	Magnesium sulfate	1.0	1.2	1.0	1.0	1.0	1.0
Antifreezing agent	Ethylene glycol	10.0	12.0	10.0	10.0	10.0	10.0
Tota	11	100.0	100.0	100.0	100.0	100.0	100.0
MA of vegetable	oil	3.81	4.50	3.81	3.81	2.91	5.76
RA of antioxida	nt	0.03	0.04	0.06	0.06	0.04	0.08
	-		- 0.4	- 0.6	- 0.6	- 0.4	- 0.8
Clogging (23°C, 1 month)		G	G	М	G	N	G
Clogging (40°C, 1 month)		G ·	G	NG	G	NG	G
Offset (23°C, 1 month)		NG	NG	G	М	-	NG
High temperature storage		G	G	G	NG	NG	G
stability (70°C, 1 week)							
High temperature storage		G	G	G	NG	NG	G
stability (70°C,	1 month)						

40

45

50

10

15

20

25

30

35

IN: iodine number

MA of vegetable oil: Minimum amount of vegetable oil calculated from Formula (1)

RA of antioxidant: Required amount of antioxidant based on amount of vegetable oil

-: Impossible to evaluate due to clogging

[0043] It was found that the ink samples of the examples all had shelf stability and provided the printed matter with preferable printing images even after being left under these predetermined conditions. On the other hand, a decrease in the viscosity of the ink samples due to water evaporation could not be fully prevented and offset of printed matter was observed in Comparative Example 1 (coefficient in Formula (1) is 0.07) and Comparative Example 2 (coefficient in Formula (1) is 0.08) in which both ink samples had smaller amounts of vegetable oil than the amounts expressed by Formula (1). In Comparative Example 3, because the amount of antioxidant in the ink was not enough with respect

to the amount of vegetable oil, the vegetable oil was oxidized too much and clogging occurred after the ink was left at 40°C for one month. The ink of Comparative Example 4 containing too much antioxidant with respect to the amount of vegetable oil had poor shelf stability, because the oxidation degree of vegetable oil was too small with respect to the amount of water evaporation. Furthermore, the ink of Comparative Example 5 containing a vegetable oil with too high iodine number and the ink of Comparative Example 6 containing a vegetable oil with too low iodine number could not properly control the oxidation of vegetable oil and preferable results were not obtained, although both amounts of each vegetable oil satisfied the Formula (1) and contained the necessary amounts of antioxidant with respect to the amounts of vegetable oil.

[0044] The present disclosure relates to subject matter contained in Japanese Patent Application No. 2001-018705, filed on January 26, 2001, the disclosure of which is expressly incorporated herein by reference in its entirety.

[0045] It is to be noted that, besides those already mentioned above, many modifications and variations of the above embodiments may be made without departing from the novel and advantageous features of the present invention. Accordingly, all such modifications and variations are intended to be included within the scope of the appended claims.

Claims

10

15

20

25

1. An emulsion ink for stencil printing comprising 20 to 50 wt.% of an oil phase and 50 to 80 wt.% of a water phase, wherein the emulsion ink contains in the oil phase at least one kind of a vegetable oil with an iodine number ranging from 110 to 150 at least in an amount indicated by the following formula in wt.%, and an antioxidant in an amount

ranging from 1 to 10 wt.% based on the content of the vegetable oil:

Minimum amount of vegetable oil in wt.% = amount of

water in ink in wt.%  $\times$  (100/iodine number)  $\times$  0.09.

2. A printed matter printed by the emulsion ink for stencil printing according to claim 1.

30

35

40

45

50

55



# **EUROPEAN SEARCH REPORT**

EP 02 00 0173

ategory	Citation of document with indicatio of relevant passages	n, where appropriate,	Relevant to claim	CLASSIFICATION OF THE APPLICATION (INLCI.7)
	US 5 800 599 A (ASADA K 1 September 1998 (1998-			C09D11/02
•	US 6 165 258 A (ASADA KI 26 December 2000 (2000-			
,D	DATABASE WPI Section Ch, Week 199847 Derwent Publications Ltd Class GO2, AN 1998-55128 XPOO2197644 & JP 10 245516 A (TOHOKI 14 September 1998 (1998- * abstract *	84 U RIKO KK), -09-14)		
				TECHNICAL FIELDS SEARCHED (Int.CI.7)
				C09D
	The present search report has been dr	rawn up for all claims	1	
	Place of search	Date of comptetion of the search	<del>'                                    </del>	Existing
	THE HAGUE	26 April 2002	Mil	ler, A
X : part Y : part doci A : lech	ATEGORY OF CITED DOCUMENTS icularly relevant if taken alone loularly relevant if combined with another ument of the same category inological background —written disclosure	T : theory or princip E : earlier patent do after the filling de D : document cride L : document cride  & : member of the s	ite in the application for other reasons	

EPO FORM 1503 03 82 (P04C01)

# ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 02 00 0173

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of Information.

26-04-2002

	Patent docume cited in search rep		Publication date		Patent family member(s)	Publication date
US	5800599	A	01-09-1998	JP	10168372 A	23-06-1998
US	6165258	Α	26-12-2000	JP CN	2000017215 A 1234420 A	18-01-2000 10-11-1999
JP	10245516	Α	14-09-1998	NONE		
						,
					•	

For more details about this annex : see Official Journal of the European Patent Office, No. 12/32